



Tropic Divan DELICARE

Item number 34107, KMAT 61000333















Product description

The Tropic curtain is part of the Care.Collection. With great attention to detail and special attention to design and function, we have put together this collection for the care sector, which is based on the idea of healing architecture and inspired by the idea of biophilic design. The Tropic curtain is part of the Care.Collection.Tropic Divan DELICARE is a large, refreshing leaf design in watercolor technique in a dense arrangement.DELICARE was specially developed for the care sector and stands for antimicrobial and air-purifying curtain fabrics. These are available on request from a minimum quantity of 100 m with a DELICARE finish, which is retained even after multiple washes .

Technical Details

Weight je m²approx. 90 g/m²Rapport Width55Compositionlength approx. 73 cm, width approx. 55 cmFlame retardancyIMO 2010 FTP Code Part 7, EN 13773, DIN 4102 / B1, DIN 4102 / B2, BS 5867 Typ C Flammability performance is dependant on the foam used.Light fastnessnote 4-5Wash fastness 40°C DIN EN ISO 105-C06note 4-5	Fabric width	approx. 300 cm
length approx. 73 cm, width approx. 55 cm 100% Polyester Trevira CS IMO 2010 FTP Code Part 7, EN 13773, DIN 4102 / B1, DIN 4102 / B2, BS 5867 Typ C Flammability performance is dependant on the foam used. Light fastness note 4-5 Wash fastness 40°C note 4-5	Weight je m²	approx. 90 g/m²
Composition 100% Polyester Trevira CS IMO 2010 FTP Code Part 7, EN 13773, DIN 4102 / B1, DIN 4102 / B2, BS 5867 Typ C Flammability performance is dependant on the foam used. Light fastness note 4-5 Wash fastness 40°C note 4-5	Rapport Width	55
Flame retardancy IMO 2010 FTP Code Part 7, EN 13773, DIN 4102 / B1, DIN 4102 / B2, BS 5867 Typ C Flammability performance is dependant on the foam used. Light fastness note 4-5 Wash fastness 40°C note 4-5		length approx. 73 cm, width approx. 55 cm
4102 / B2, BS 5867 Typ C Flammability performance is dependant on the foam used. Light fastness note 4-5 Wash fastness 40°C note 4-5	Composition	100% Polyester Trevira CS
Light fastness note 4-5 Wash fastness 40°C note 4-5	Flame retardancy	•
Wash fastness 40°C note 4-5		Flammability performance is dependant on the foam used.
	Light fastness	note 4-5
DIN EN ISO 105-C06	Wash fastness 40°C	note 4-5
	DIN EN ISO 105-C06	



Wash fastness 60°C DIN EN ISO 6330 DIN EN ISO 5077	note 4-5
Dimensional change Washing 40°C DIN EN ISO 6330 DIN EN ISO 5077	warp approx. +/-1%, weft approx. +/-1%
Dimensional change Washing 60°C DIN EN ISO 6330 DIN EN ISO 5077	warp approx. +/-1%, weft approx. +/-1%
Rubbing fastness DIN EN ISO 105-X12	dry: note 4, wet: note 4-5
Care labelling	
State	2024-04-25